

# Study of Graphenic Carbon Powder Interaction with TiO<sub>2</sub> Grown by RF Sputtering and Effect on the Photocatalytic Activity

Hafeez Ullah, Francesca Marchetti, Nadhira Laidani\*

Fondazione Bruno Kessler, Centro Materiali e Microsistemi, Via Sommarive 18, 38123 Trento, Italy  
laidani@fbk.eu

TiO<sub>2</sub> nanoparticles were deposited by RF sputtering onto powders made of graphenic carbon flakes. The influence of the RF power during the sputtering process was investigated, with a focus on the interaction of this powder with titanium dioxide. i.e. the electronic properties change at the interface between the carbon support and the oxide and the structural modifications of the support. X-ray photoelectron spectroscopy was employed for such a purpose. It was found that the C 1s core level binding energy in the graphenic powder shifted to lower binding energies values upon the deposition of the TiO<sub>2</sub> nanoparticles. Such a downshift was observed on Ti2p and O1s core levels too and increased with rising of TiO<sub>2</sub> amount. The downshift of the C 1s core level indicates a charge transfer from graphene to TiO<sub>2</sub> nanoparticles due to the lower work function of carbon relatively to that of TiO<sub>2</sub>, with a lowering of the Fermi level. The graphenic powder - supported TiO<sub>2</sub> nanoparticles showed an improvement of the photocatalytic activity towards methyl red molecule degradation under solar light.

## 1. Introduction

Recently TiO<sub>2</sub> nanostructures and graphene sheets were extensively studied for the high performance of the photo-catalytic activity of graphene-TiO<sub>2</sub> composite and also to improve other properties of graphene. It has been well established that graphene as a catalyst support has high potential for the improvement of the photocatalytic activity due to its unique properties, such as high surface area, high transparency, high electrical conductivity and good interfacial contact with adsorbents [Park et al. 2008; Kim et al. 2011]. Different chemical and physical approaches were used to prepare the TiO<sub>2</sub> nanostructures onto graphene, such as the one step hydrothermal method for a reduced graphene oxide-TiO<sub>2</sub> nanostructure composite without using reducing agent [Sher Shah et al. 201]. They measured the photocatalytic activity of the prepared composite for the degradation of rhodamine B dye and of a colorless dye like benzoic acid, under visible light. The same method was adopted to obtain a graphene-TiO<sub>2</sub> composite tested for its photocatalytic performance towards the degradation of rhodamine B, methylene blue and methyl orange under UV light irradiation [Gu et al. 2016]. A hydrothermal method used for the preparation of the TiO<sub>2</sub> -graphene composite resulted in a high photocatalytic activity for the degradation of sodium pentachlorophenol [Zhang et al. 2009].

Studies showed that the graphene-TiO<sub>2</sub> composite structure is characterized by particular interface electron properties where a charge transfer occurs. The charge transfer phenomenon between the graphene and TiO<sub>2</sub> has been explained by Du et al. [Du et al. 2011] by using ab initio calculations, the charge being transferred from graphene to TiO<sub>2</sub> as the consequence of large work function difference, which leads to significant hole doping of graphene.

In this work, the results of a study of TiO<sub>2</sub> particle decoration of graphenic carbon powder are presented, with a focus on the modification of the electronic properties of the graphenic powder at the interface with the nanoparticles, the structural changes of the carbon-based powder and on the oxide nanoparticles. The TiO<sub>2</sub> nanoparticles were grown onto graphenic flakes by radio-frequency (RF) sputtering, a “dry” method in contrast with the “wet” method so far generally used. The decorated powder was tested for its photocatalytic activity towards methyl red organic molecule.

## 2. Experimental details

### 2.1 Sample preparation

Commercial graphenic powder was purchased in Graphene Supermarket (Grade AO-1). The average flake thickness and lateral size values provided by the supplier were 1.6 nm and 10  $\mu\text{m}$  ca. respectively, with a specific surface area given as (400 – 800)  $\text{m}^2/\text{g}$ . Prior and after the oxide deposition, the graphenic powders were handled in a glove box where they were protected from the moisture and other kinds of the contamination. No further powder processing was applied.

### 2.2 Deposition

The anatase  $\text{TiO}_2$  nanoparticles were deposited onto the graphenic powder by RF sputtering in argon plasma. A high purity (99.99 %) 5 cm diameter  $\text{TiO}_2$  disc was used as a sputtering target. The distance between the  $\text{TiO}_2$  target and graphene powder were fixed at 50 mm. A powder vibration system was used during the deposition process to uniformly decorate the graphene powder with  $\text{TiO}_2$  nanoparticles. The RF power was varied between 30 W and 80 W, corresponding to a target self-bias voltage in a range between -174 and -294 V. The process pressure and the powder vibration frequency and amplitude were kept constant at 6 Pa and 20 Hz and 32  $\mu\text{m}$  respectively. The deposition time was fixed at 40 min.

### 2.3 Characterization

X-ray photoelectron spectroscopy (XPS) analysis was performed with a Scienta 200 instrument, using a monochromatic  $\text{AlK}\alpha$  X-ray source (1486.6 eV). The high-resolution (0.4 eV) spectra of C1s, O1s and Ti2p core lines were acquired at 150 eV pass energy. The binding energies (BEs) were referenced to the Fermi level. The core line spectra were fitted with a Gauss-Lorentz peak shape, after a Shirley-type background subtraction, using a software based on RStudio [Speranza and Canteri 2019]. The atomic ratio values between elements were determined from the area ratio of selected core level peaks corrected by the sensitivity factors of the latter. The sample morphology before and after decoration was investigated by transmission electron microscopy (TEM).

### 2.4 Photo-activity test

The photocatalytic activity of the decorated powder was studied by measuring the degradation kinetics of methyl red (MR) molecules in a solution of 16  $\mu\text{M}$  MR in presence of an 8mM Tris-HCl buffer (pH 8.2). Quartz cuvettes containing 2.55 ml suspensions (with a powder concentration of 23,3  $\mu\text{g}/\text{ml}$ ) were placed over a waving platform shaker to allow the solution to get in contact with the powder surface and to avoid the sedimentation of the powder over time. The solutions received perpendicularly the light irradiation from a solar simulator set at the power of 1 sun (1  $\text{kW}/\text{m}^2$ ). The absorbance spectra of the methyl red solutions are acquired over the UV-Visible range (200–800 nm) using a Cary 100 spectrophotometer, after regular time intervals. To monitor the dye degradation kinetics, the absorbance value at 430 nm wavelength (corresponding to maximum absorbance of the MR molecule in the visible light range) was followed.

## 3. Results and Discussion

By the variation of the RF power values, different amounts of  $\text{TiO}_2$  nanoparticles onto graphene were obtained. The influence of the  $\text{TiO}_2$  concentrations on the chemical and electronic properties of the graphenic sheets is discussed. The morphology of the decorated powder and its interaction with the  $\text{TiO}_2$  nanoparticles were characterized by TEM and XPS respectively.

### 3.1 Surface morphology of the decorated graphene with sputtered $\text{TiO}_2$

Figure1 shows the decorated graphene with  $\text{TiO}_2$  nanoparticles deposited at 80 W, as acquired by TEM analysis. Very small  $\text{TiO}_2$  nanoparticles anchored onto graphene can be observed. Graphene sheets were decorated with a high coverage of  $\text{TiO}_2$  nanoparticles and the deposited particles are well distributed over the graphene sheets. The size of the deposited  $\text{TiO}_2$  nanoparticles was in the range of (5-10) nm. For such specimen, approximately 75% of the powder surface was covered by the oxide.




Figure 1: TEM image of deposited  $\text{TiO}_2$  nanoparticles onto the graphenic sheets composing the powder.

### 3.2 XPS analysis undoped graphene and $\text{TiO}_2$ doped graphene deposited at different RF power values

The high resolution XPS spectra of the C 1s core level of the undecorated and decorated powder with  $\text{TiO}_2$  nanoparticles deposited at different power values are shown in Figure 2(a). The C 1s core level spectra were fitted by three components, centred at the following BE: 284.45, 285.23 and 286.2 eV, which are attributed to C-C ( $\text{sp}^2$ ), C-H/C-C ( $\text{sp}^3$ ) and C-O bonds respectively. It was observed that the C 1s core level of the graphene shifted toward lower BE values by depositing  $\text{TiO}_2$  nanoparticles onto the powder. The main component relative to  $\text{sp}^2$ C-C bonding shifted by -0.04 eV for a 30W power and continued down-shifting by raising the RF power values to reach -0.17 eV for 80 W.




Figure 2: XPS spectra for graphenic powder and deposited  $\text{TiO}_2$  nanoparticles at different RF power values (a) C 1s core levels with marked positions of the C-C ( $\text{sp}^2$ ) bond (b) Ti 2p core level spectra.

The BE reduction of the C 1s core level after the deposition of  $\text{TiO}_2$  nanoparticles can be understood as a p-doping of the graphenic sheets, whereas the electrons are transferred from graphene to  $\text{TiO}_2$  nanoparticles at the interface, resulting in a lowering of the Fermi level in the graphene sheets. Recently it was reported that due to the interaction of graphene with a high band gap semiconductor, the C 1s core level binding energy reduced to lower values due to the charge transfer at the interface in order to align the Fermi level and to the difference of the work function values [Joucken et al. 2014; Geng et al. 2008]. Similar observation about the charge transfer between graphene and  $\text{TiO}_2$  due to large difference in work function values between the  $\text{TiO}_2$  (5.50 eV) and graphene (4.3 eV) is reported by Du et al, using density function theory [Du et al. 2011].

The Ti 2p spectra for the decorated powder at different RF power values are presented in Figure 2(b), showing the peak fitting by two components, at 459.08 eV and 464.95 eV corresponding to Ti  $2p_{3/2}$  and Ti

2p<sub>1/2</sub> in TiO<sub>2</sub> (Diebold 2003). Similar to the C1s spectra, with increasing the RF power values, the Ti 2p peaks shifted towards the lower binding energy values, with a maximum downshift of - 0.26 eV for 80 W.

Figure 3(a) depicts the O 1s spectra for the deposited TiO<sub>2</sub> nanoparticles onto the graphenic powder at different power values. The O 1s XPS spectra were fitted by three components, the main one located at 530.7 eV BE and assigned to O<sup>2-</sup> bound to Ti<sup>+4</sup> [Safeen 2015]. Two minor components, located at 532.12 eV and 533.3 eV, can be attributed to the C–OH and C–O bonds respectively [Luciu 2012a; Luciu et al. 2012b].

The atomic ratio Ti/C determined as the area ratio between the main C1s component and the Ti2p<sub>3/2</sub> peak, corrected by the corresponding sensitivity factor. Similarly, the oxide stoichiometry (O/Ti) was measured on the basis of the area under the main component of the O1s spectra and that under the Ti 2p<sub>3/2</sub> component. The Ti/C and the O/Ti, atomic ratios are plotted in function of the applied RF power in Figure 3 (b), where it can be observed the increase of Ti/C with the RF power increase and the O/Ti decrease from 1.96 to 1.86 when the applied power raised from 30 W to 80 W. The deposited oxide grew more oxygen deficient at high RF power values.




Figure 3: XPS O 1s core peak of decorated graphenic powder(a) and variations of Ti /sp<sup>2</sup>C and O/Ti atomic ratio (oxide stoichiometry in function of the applied RF power for sputtering (b).

### 3.3 Photocatalytic activity of the decorated powder

The photocatalytic activity study of the undecorated and decorated graphenic powder with TiO<sub>2</sub> nanoparticles with an atomic ratio (Ti/C sp<sup>2</sup> = 13.4 at.%) grown at 80 W was carried towards methyl red (MR) dye degradation as a model reaction under simulated solar light.

Figure 4(a) shows the photo catalytic activity in terms of the variation of the MR concentration, (C), in the test solution in function of the exposition time to solar light, normalized to the initial concentration at time t=0 (C<sub>0</sub>). This normalized concentration (C/C<sub>0</sub>) is taken equal to the normalized MR absorbance to the initial absorbance at time t=0, (A/A<sub>0</sub>).

It was observed that the variation of the degradation level of MR molecules in presence of the graphenic powder is comparable to that of MR itself (within the ± 0,025 error limits), implying that the powder had no intrinsic catalytic activity. The degradation of MR was enhanced in the presence of the powder-TiO<sub>2</sub> composite, containing 13.4 at.% Titanium oxide by about 30%. According to a first-order degradation kinetics at low dye concentration [Al-Ekabi and Serpone,1988], following the equation  $C/C_0 = e^{-kt}$ , the rate constant k can be determined by plotting Ln(C/C<sub>0</sub>) in function of time (Figure 4(b)). It was found equal to  $1.5 \times 10^{-3} \text{ min}^{-1}$  for the TiO<sub>2</sub>/graphenic powder sample obtained with 80W power. For comparison and assuming the same kinetics regime for a 75 nm continuous TiO<sub>2</sub> film onto a silicon substrate, tested in the same MR solution conditions, a value of  $k=1,73 \times 10^{-4} \text{ min}^{-1}$  was found.

It is reported that three factors are important for the photocatalytic process, that is, the charge separation and transportation, absorption of light and the adsorption of the pollutant molecules [Yang et al. 2016]. In relation of the present graphenic powder-TiO<sub>2</sub> composite, it was also reported that the formation of the charge transfer complex at the interface of the oxide and graphene sheets would be expected to facilitate the photocatalytic activity under UV-Vis light, by facilitating a more effective charge separation between electrons and the holes

created by the electron excitation, and reducing e-hole recombination events [Park et al. 2009; Seo et al. 2005]. Furthermore, the present XPS results showed that the deposited oxide nanoparticles were under-stoichiometric, (best described as  $\text{TiO}_{2-x}$ ). It is well assumed that such oxygen vacancies in the  $\text{TiO}_2$  nanoparticle can enhance the photocatalytic activity of the  $\text{TiO}_2$ . The oxygen vacancies in the  $\text{TiO}_{2-x}$  generate localized states within the band gap, ranging from 0.75 to 1.18 eV below the conduction band and were reported to lead to a photo-response to the light irradiation [Emeline et al. 2008].

The contribution of graphenic carbon to the photocatalytic activity of  $\text{TiO}_2$  may be explained by the offered higher specific surface area, the more conductive nature and the lower work function of the graphenic carbon powder and the higher absorbance in the visible part of the solar spectrum. However, these characteristics are not exclusively pertaining to graphenic carbon but to other carbon forms too. In fact, this question was initially addressed by Zhang et al. [Zhang et al. 2010] as to whether the role of graphene in enhancing  $\text{TiO}_2$  photoactivity is fundamentally different from that of carbon nanotubes, fullerene and activated carbon, pointing towards rather a negative answer. More investigation, by taking into account all the complexity and intercorrelation of the key parameters influencing the photocatalytic activity, as well as the structure (such as disorder, defects, doping) of the considered graphenic carbon itself, is still needed to answer this question.




Figure 4: (a) Normalized dye concentration ( $C/C_0$ ) time variation under solar light exposure of decorated graphenic carbon powder with  $\text{TiO}_2$  nanoparticles at 80 W, uncoated powder and methyl red (b)  $\ln(C/C_0)$  - Time plot for the determination of the rate constant as the slope of the data linear fit, for the powder decorated at 80 W.

#### 4. Conclusion

The influence of the  $\text{TiO}_2$  concentration on the chemical and photocatalytic activity of the decorated graphene sheets was discussed. The particle nature of the deposited  $\text{TiO}_2$  was confirmed by TEM examination. The XPS analysis further showed the p-doping of graphene upon the deposition of the  $\text{TiO}_2$  nanoparticles, whereas the C 1s core level binding energy downshift was evidenced. The well dispersed  $\text{TiO}_2$  nanoparticles onto the graphenic powder used as a catalyst support showed photocatalytic activity towards MR degradation.

#### Acknowledgments

The authors wish to thank Gloria Ischia and Marina Scarpa, from the University of Trento, for the TEM analysis and for the support and the use of the solar simulator equipment, respectively.

H. Ullah's present affiliation: Institute of Physics & Electronics, Gomal University, Dera Ismail Khan 29220, KP, Pakistan. F. Marchetti's present affiliation: Protec Surface Technologies Srl, via Benaco 88, 25081 Bedizzole, Italia.

#### References

- Al-Ekabi H., Serpone N., 1988), Photocatalytic degradation of chlorinated phenols in aerated aqueous solutions over  $\text{TiO}_2$  supported on a glass matrix, *Journal of Physical Chemistry* 92(20), 5726-5731.
- Diebold U., 2003, The surface science of titanium dioxide, *Surface Science Reports* 48, 53-229.

- Du A., Hau Ng Y. H., Bell N. J., Zhu Z., Amal R, and Smith S. C., 2011, Hybrid graphene/titania nanocomposite: interface charge transfer, hole doping, and sensitization for visible light response. *The Journal of Physical Chemistry Letters* 2, 894-899.
- Emeline A. V., Kuznetsov V. N., Rybchuk V. K. and Serpone N, 2008, Visible-light-active titania photocatalysts: the case of N-doped TiO<sub>2</sub>s—properties and some fundamental issues, *International Journal of Photoenergy*, 1-19.
- Geng H.-Z., Kim K. K, Song C., Xuyen N. T., Kim S. M., Park K. A., Lee D. S., An K. H., Lee Y. S., Chang Y., Lee Y. J., Choi J. Y., Benayad A. and Lee Y. H. , 2008, Doping and de-doping of carbon nanotube transparent conducting films by dispersant and chemical treatment. *Journal of Materials Chemistry* 18, 1261-1266.
- Gu L., Zhang H., Jiao Z., Li M., Wua M. and Lei Y., 2016, Glucosamine-induced growth of highly distributed TiO<sub>2</sub> nanoparticles on graphene nanosheets as high-performance photocatalysts. *RSC Advances* 6, 67039-67048.
- Joucken F., Tison Y., Le Fèvre P.,Tejeda A.,Taleb-Ibrahimi A., Conrad E., Repain V., Chacon C., Bellec A., Girard Y., Rousset S., Ghijsen J., Sporken R., Amara H., Ducastelle F. and Lagoute J. ,2014, Charge transfer and electronic doping in nitrogen-doped graphene. *Scientific reports* 5, 14564-14564.
- Kim H.-i., Moon G.-h., Monllor-Satoca D., Park Y. and Choi W., 2011, Solar photoconversion using graphene/TiO<sub>2</sub> composites: nanographene shell on TiO<sub>2</sub> core versus TiO<sub>2</sub> nanoparticles on graphene sheet, *The Journal of Physical Chemistry C* 116, 1535-1543.
- Luciu I. , 2012a, RF plasma synthesis and characterization of thin films for transparent conductors, PhD Thesis, University of Trento, Italy.
- Luciu I., Bartali R. and Laidani N., 2012b, Influence of hydrogen addition to an Ar plasma on the structural properties of TiO<sub>2-x</sub> thin films deposited by RF sputtering, *Journal of Physics D: Applied Physics* 45, 345302.
- Park S., Lee K.-S., Bozoklu G., Cai W., Nguyen S.T., and S. Ruoff R. S., 2008, Graphene oxide papers modified by divalent ions - enhancing mechanical properties via chemical cross-linking, *ACS nano* 2, 572-578.
- Park Y, Singh N.J., Kim K.S., Tachikawa T., Majima T., Choi W. , 2009, Fullerol–Titania Charge-Transfer-Mediated Photocatalysis Working under Visible Light, *Chemistry - A European Journal* 15(41), 10843-10850.
- Safeen K., Micheli V., Bartali R., Gottardi G. and Laidani N, 2015, Low temperature growth study of nanocrystalline TiO<sub>2</sub> thin films deposited by RF sputtering, *Journal of Physics D: Applied Physics* 48, 295201.
- Seo Y. S., Lee C., Lee K. H. & Yoon K. B, 2005, Charge-Transfer Complexes between Aromatic Hydrocarbons and Dry Titanium Dioxide. *Angewandte Chemie International Edition* 44, 910-913.
- Sher Shah, M. S. A., Park A. R., Zhang K., Park J. H. and Yoo P. J., 2012, Green synthesis of biphasic TiO<sub>2</sub>–reduced graphene oxide nanocomposites with highly enhanced photocatalytic activity, *ACS Applied Materials & Interfaces* 4, 3893-3901.
- Speranza G. and Canteri R., 2019, RxpsG a new open project for Photoelectron and Electron Spectroscopy data processing, *SoftwareX*, 10, 100282.
- Yang Y., Xu, L., Wang H., Wang W. & Zhang L., 2016, TiO<sub>2</sub>/graphene porous composite and its photocatalytic degradation of methylene blue, *Materials & Design* 108, 632-639.
- Zhang, H., Lv X., Li Y., Wang Y. and Li J, 2009, P25-graphene composite as a high performance photocatalyst. *ACS Nano* 4, 380-386.
- Zhang Y., Tang Z.-R., Fu X. and Xu Y.-J., 2010, TiO<sub>2</sub>\_Graphene Nanocomposites for Gas-Phase Photocatalytic Degradation of Volatile Aromatic Pollutant: Is TiO<sub>2</sub>\_Graphene Truly Different from Other TiO<sub>2</sub>\_Carbon Composite Materials?, *ACS Nano* 4 (12), 7303 – 7314.